

C&R/AFL Laboratory
 Malledijk 18
 P.O.Box 200
 3200 AE Spijkenisse
 Dir Tel +31 (0)88 214 45 15
 Email: nl.consumerproducts@sgs.com

Capventure bv
 Attn: de heer Maaik Clewits
 van Leijenberghlaan 199-E
 1082GG Amsterdam
 The Netherlands

ANALYTICAL REPORT SP19-030795

The analysis of the sample said to be : Consumer Products

Article description : Zuperzozial Cruising Travel mug
 Reference : 1401202
 Batch no : #(2018)40006
 Date sample received : 13-08-2019
 Testing Period : 15-08-2019 till 19-08-2019

<u>Sample</u>	<u>Description</u>
001	Zuperzozial Coffee mug



<u>Test Requested</u>	<u>Method</u>	<u>Result</u>
Specific Migration of Formaldehyde from Plastic	0004-S	PASS
Specific Migration of Melamine from Plastic	0004-S	PASS

Report no.: SP19-030795
 Page 1 of 3

Unless otherwise agreed, orders are executed in accordance with the latest version of the SGS Nederland (the Company) General Conditions. Upon simple request the conditions will again be sent to you. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Specific Migration of Formaldehyde from Plastic

(0004-S)

Method: EN13130-1:2004. The test is performed by HPLC-UV.

	001	-
	Result	limit
Contact	3rd contact	-
Simulant	Acetic Acid 3%	-
Temperature (°C)	70	-
Contact Time (hrs)	2	-
Surface area/Volume ratio (dm ² /l)	5,1	-
Specific Migration of Formaldehyde (mg/kg)	9,1	15
Conclusion Specific Migration Formaldehyde	PASS	-

Test results indicate that the sample(s) do(es) meet the requirements with regard to specific migration of formaldehyde of European Regulation 10/2011 including amendments.

Specific Migration of Melamine from Plastic

(0004-S)


Method: EN13130-1:2004. The test is performed by HPLC-UV.

	001	-
	Result	limit
Contact	3rd contact	-
Simulant	Acetic Acid 3%	-
Temperature (°C)	70	-
Contact Time (hrs)	2	-
Surface area/Volume ratio (dm ² /l)	5,1	-
Specific Migration of Melamine (mg/kg)	1,641	2,5
Conclusion Specific Migration Melamine	PASS	-

Test results indicate that the sample(s) do(es) meet the requirements with regard to specific migration of melamine of European Regulation 10/2011 including amendments.

Sample: 001

Description: Zuperzozial Coffee mug



Spijkernisse, 19 August 2019
C&R/AFL Laboratory

E.A.M. van Meurs
Laboratory Manager

Report no.: SP19-030795
Page 3 of 3

Unless otherwise agreed, orders are executed in accordance with the latest version of the SGS Nederland (the Company) General Conditions. Upon simple request the conditions will again be sent to you. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.